

ABSTRACT OF DISCLOSURE

A textile having high fluorine adhesion rate, and excellent water- and oil-repellency can be obtained by a method of producing a treated textile, comprising steps of:

5 method of producing a treated textile, comprising steps of:

(1) preparing a treatment liquid comprising a water- and oil-repellent agent which comprises at least one fluorine-containing compound selected from the group consisting of a fluorine-containing polymer or a fluorine-containing low

10 molecular weight compound, (2) adjusting pH of the treatment liquid to at most 7, (3) applying the treatment liquid to a textile, (4) treating the textile with steam, and (5) washing the textile with water and dehydrating the textile, wherein the treatment liquid comprises a water-

15 soluble cationic polymer.